


## Description

OETechCP is a mixture of reactive polyurethane oligomers dissolved in organic solvents.

## Areas of Application

OETechCP is used to improve the adhesion of OETech Urethanes on glass with ceramic frits and provide for OEM specifications.



## Technical Data

Color	Viscosity	Density At 68 °F	Conventional Solids Content (EN 827)	Application Temperature	Specific Data
Black	100 mLDIN cup, Ø = 4 mm : 12 to 15 mPa.s	0.90 ±0.05	26.5 ±1.5 %	41 to 95 °F Drying time	Drying time at 68°F : 10 to 15 min

## Instructions for Use

Substrates preparation :

The substrates to be coated must be flat, dry, dust free and not have any traces of grease or other contaminants that could adversely affect the bonding performance. Degrease ceramic silk-screen printing with a solvent such as acetone. When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by the manufacturer or supplier. OETech CP is a metal primer to be applied to freshly painted pinchwelds or bare metal scratches prior to urethane application.

OETech CP can also be applied to glass parts that do not have a UV protective frit to prevent UV degradation of the urethane bond.

Application :

Thoroughly shake the product before use. Hermetically seal the container immediately after use. Any contact with humidity will make the primer cure. Apply the primer on the silk-screen printing by a lint-free felt dauber with a uniform and light pressure in order to get a homogenous and dull film.

## Storage and Shelf Life

12 months in unopened original packaging stored in dry premises between 32 and 95°F.

## Packaging

6 – 4 oz aluminum bottles per case.

## Safety

Harmful and highly flammable. Read material safety data sheet before use.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired.

Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product.

Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

**See also material safety data sheet.**